

AMENDMENTS TO THE CLAIMS

1-5 (Canceled)

6. (Currently Amended) A composition in accordance with claim ~~4~~ 25, wherein the said pozzolan has a P.S.D. such that at least 95% by weight of the particles are of less than 25 microns E.S.D.

7. (Currently Amended) A composition in accordance with claim ~~4~~ 25, wherein the said pozzolan has a P.S.D. such that at least 95% by weight of the particles are of less than 10 microns E.S.D.

8. (Currently Amended) A composition in accordance with claim ~~4~~ 25, wherein the said pozzolan has a P.S.D. such that at least 95% by weight of the particles are of less than 5 microns E.S.D.

9. (Currently Amended) A composition in accordance with claim ~~4~~ 25, wherein the said pozzolan has a P.S.D. such that at least 95% by weight of the particles are of less than 3 microns E.S.D.

10. (Canceled)

11. (Currently Amended) A blended pozzolanic cement produced by blending with portland cement, from 5 to 40% by weight of the total composition of a fine white pozzolan

comprising a finely ground vitreous ~~low alkali low iron glass derived from glass~~
manufacturing by products calcium aluminosilicate (CaO-Al₂O₃-SiO₂) powder derived from
previously discarded glass fibers having low alkali and low iron content, and low levels of
discolorants;

said powder having a alkali content by weight of not more than 2% as (Na₂O+K₂O),
an iron content by weight of not more than 0.8% as Fe₂O₃, and being substantially white in
color with a reflectance value of at least 80 as measured by a Technibrite TB-1C colorimeter
according to the ISO 2467, 2471 method;

at least 95% by weight of the powder particles being of less than 45 microns E.S.D.
and said particles having a blocky, relatively equi-dimensional particle shape wherein the
average aspect ratio of the particles is less than 2:1, and with substantially no residual high
aspect ratio fibers.

12. (Previously Presented) A blended cement in accordance with claim 11 which is
substantially white; said cement having a reflectance of at least 80 on an "Rd" scale measured
on a Hunter Lab colorimeter.

13. (Currently Amended) A white pozzolanic cement produced by intergrinding of a vitreous
low alkali, low iron pozzolan ~~derived from glass manufacturing by products~~ in accordance
with claim 25 with white portland cement clinker and white gypsum.

14. (Currently Amended) A raw feed for white cement clinker production comprising a
finely ground vitreous low alkali, and low iron content ~~glass pozzolan~~ in accordance with
claim 25 derived from fine grinding of glass fibers.

15. (Currently Amended) A white pozzolanic cement in accordance with claim 13, wherein said white clinker is selected from one or more members of the group consisting of Type I, Type II, Type III, Type IV, ~~or~~ and Type V ASTM C-150 cements.

16. (Currently Amended) A colored pozzolanic cement comprising the white cement of claim 12 together with an admixed coloring pigment.

17. (Previously Presented) A blended pozzolanic cement in accordance with claim 11, further comprising one or more functional cement additives selected from the group consisting of accelerators, retarders, water-reducers/plasticizers, corrosion inhibitors, and pigments.

18. (Withdrawn) A process for converting glass fiber wastes into high quality filler and pozzolan products, comprising shredding long entangled strands of low alkali and low iron content vitreous glass fibers into short fibers, adjusting the moisture content of the short fibers, grinding the short moisture adjusted fibers, and classifying the ground material to produce a uniform high quality substantially white product with precise control over the maximum particle size and particle size distribution.

19. (Withdrawn) A process in accordance with claim 18, wherein the waste glass fibers have by weight an alkali content of less than 2%, and an iron content of less than 0.8%.

20. (Withdrawn) A process in accordance with claim 19, wherein said shredding provides short glass fibers of less than 5 mm.

21. (Withdrawn) A method in accordance with claim 20, wherein said shredded and moisture adjusted short fibers are ground in a vertical attrition mill using an energy input of at least 100 kW/hrs/ton of said fibers.

22. (Withdrawn) A process in accordance with claim 21, wherein said shredded short fibers have an adjusted moisture content of less than 10% by weight.

23. (Withdrawn) A process in accordance with claim 22, wherein said shredded short fibers have an adjusted moisture content of less than 2% by weight.

24. (Withdrawn) A process in accordance with claim 22, wherein said shredded short fibers have an adjusted moisture content of 0.5 to 1.0% by weight.

25. (New) A white pozzolan for blending with portland cement for use in white and colored concrete applications, comprising a finely ground vitreous calcium aluminosilicate ($\text{CaO}-\text{Al}_2\text{O}_3-\text{SiO}_2$) powder derived from previously discarded glass fibers having low alkali and low iron content, and low levels of discolorants;

said powder having a alkali content by weight of not more than 2% as ($\text{Na}_2\text{O}+\text{K}_2\text{O}$), an iron content by weight of not more than 0.8% as Fe_2O_3 , and being substantially white in color with a reflectance value of at least 80 as measured by a Technibrite TB-1C colorimeter according to the ISO 2467, 2471 method;

at least 95% by weight of the powder particles being of less than 45 microns E.S.D. and said particles having a blocky, relatively equi-dimensional particle shape wherein the average aspect ratio of the particles is less than 2:1, and with substantially no residual high

aspect ratio fibers.